




HONEYCOMBS CERAMICS B.V.

RTO Ceramic Media

DATA SHEET OF HEAT TRANSFER MEDIA

DENSE ALUMINA HONEYCOMBS WITH SQUARE FEET



1. Production Properties

Standard Size	150x150x300mm, 150x150x150mm	
Cell Count	40x40 cells	50x50 cells
Cell Size	3.0x3.0 mm	2.37x2.37 mm
Wall Thickness	0.7 mm	0.6 mm
Min.	0.65	0.5
Max.	0.75	0.7
Average Piece Weight (150x150x300mm)	5.2 kg	5.3 kg
Typical Density	760 kg/m ³	780 kg/m ³
Free Volume	64 %	62.4 %
Surface Area	825 m ² /m ³	1050 m ² /m ³

PDS_001_ Dense Alumina Honeycomb With Square Feet

Date of issue: September 2017

This document contains information that is subject to the copyright of HONEYCOMBS CERAMICS B.V.

None of the information shall be used, copied or replicated without the written permission of HONEYCOMBS CERAMICS B.V., The Netherlands.



HONEYCOMBS CERAMICS B.V.

RTO Ceramic Media

2. Chemical Properties(Test Standard: GB/T4734-1996)

<u>Chemical Composition</u>	Typical Data (Wt%)
Al ₂ O ₃	67.9
SiO ₂	26.8
TiO ₂	0.34
Fe ₂ O ₃	0.89
K ₂ O + Na ₂ O	2.57
CaO	0.71
MgO	0.65

3. Physical Properties (Test Standard: JCT 2135-2012)

	Typical
Material Density	2.67 g/cm ³
Apparent density	2.13 g/cm ³
Water Absorption	9.46 %
Acid Resistance Strength Wt. Loss	1 %
Maximum Working Temperature	1450 °C
Coefficient of Thermal Expansion	6.2 x10 ⁻⁶ /°C
Impact Thermal Resistance	≥300 °C/min
Specific Heat (20-1000 °C)	998 J/Kg.K
Thermal Conductivity (20-1000 °C)	2.42 W/m.k

PDS_001_Dense Alumina Honeycomb With Square Feet

Date of issue: September 2017

This document contains information that is subject to the copyright of HONEYCOMBS CERAMICS B.V.

None of the information shall be used, copied or replicated without the written permission of HONEYCOMBS CERAMICS B.V., The Netherlands.



HONEYCOMBS CERAMICS B.V.

RTO Ceramic Media

4. Dimension Tolerance (Test Standard: JCT 2135-2012)

Item		Tolerance	
Cell Number		± 2 cells/100cm ²	
Cell Size		$\pm 10\%$	
Size Tolerance	Width/ Length	w (h) < 100mm	± 1.5 mm
		100mm < w (h) \leq 150mm	± 2.0 mm
		150mm < w (h) \leq 250mm	± 3.0 mm
	Height	L \leq 100mm	± 1.5 mm
		100 < L \leq 250mm	± 2.5 mm
		L > 250mm	± 3.0 mm
Aspect Deformed	End surface planeness		≤ 1.5 mm
	Side face planeness		≤ 3.0 mm
Cracking	If the height < 150mm, no flaw If the height \geq 150mm, allow exist width \leq 0.2mm, depth \leq 2 cells, length < 1/2 product length flaw one piece		
Cell's Defect	Depth > 10mm, exist \leq 0.2% total cell's number		
Wall Defect	> 5% wall length < 2 points, total defects < 4 points		

5. Packing and Transportation

1m³, 147 / 294 pieces/m³ packed in 115 x 115 x 115cm wooden Pallets.

Transportation: 20m³ in 20 crates in 20' container.

PDS_001_Dense Alumina Honeycomb With Square Feet

Date of issue: September 2017

This document contains information that is subject to the copyright of HONEYCOMBS CERAMICS B.V.

None of the information shall be used, copied or replicated without the written permission of HONEYCOMBS CERAMICS B.V., The Netherlands.